

Test Result

Test Method for Antibacterial Finishes on Textile Materials: Assessment of (AATCC TM100-2019)

Test specimen: As received

Enro - Tech 3D mask inner fabric (after 100 machine washes and tumble dry)

Test bacteria: *Staphylococcus aureus* (ATCC 6538)

Tested Specimen	Bacterial count (number of bacteria per sample) over contact period		Result: Percent reduction of bacteria	Specified requirement	Comment
	0 hour	24 hours			
As received	2.12 x 10 ⁵	1.86 x 10 ⁴	99.98%	/	/
Untreated control / Viability control	2.91 x 10 ⁵	1.01 x 10 ⁸	/	≥1 log increase	Valid

Test bacteria: *Klebsiella pneumoniae* (ATCC 4352)

Tested Specimen	Bacterial count (number of bacteria per sample) over contact period		Result: Percent reduction of bacteria	Specified requirement	Comment
	0 hour	24 hours			
As received	1.22 x 10 ⁵	5.33 x 10 ⁵	99.74%	/	/
Untreated control / Viability control	2.13 x 10 ⁵	2.07 x 10 ⁸	/	≥1 log increase	Valid

Note: The untreated control sample is standard antimicrobial test viability control fabric from International Antimicrobial Council.

Remarks:

- 1 The number of circular swatches (4.8 +/- 0.1 cm in diameter) used per jar: 5
 - 2 Sterilization of samples by autoclave: No
 - 3 Culture medium used for bacterial culture preparation: Nutrient broth
 - 4 Diluent used for inoculum dilution: 1:20 Nutrient broth with 0.05% Triton X-100
 - 5 Neutralizing solution: Dey Engley Neutralizing broth
 - 6 Percent (%) reduction of bacteria = 100(B - A)/B, where:
 A = the number of bacteria recovered from the inoculated treated test specimen swatches in the jar incubated over the 24-h contact period
 B = the number of bacteria recovered from the inoculated untreated test specimen swatches in the jar incubated over the 24-h contact period
- ***End of Report***

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.