

TEST REPORT: 7191247377-CHM20-05-RC
18 NOV 2020



PSB Singapore

RESULTS

Sample Description: Enro – Tech 3D Mask (after 100 m/c washes and tumble dry)

Test Method:
ASTM F2101

Test sample/ controls	Stage 1, CFU	Stage 2, CFU	Stage 3, CFU	Stage 4, CFU	Stage 5, CFU	Stage 6, CFU	Sum of Total plate count for the 6 sieves, CFU	Average Count for Controls, CFU	BFE (%)
-ve Control	0	0	0	0	0	0	Less than 1		
+ve Control 1	134	305	605	608	418	7	2077	2052	
+ve Control 2	114	291	570	601	438	13	2027		
Sample 1	0	0	0	0	2	3	5		99.7
Sample 2	0	0	0	0	1	4	5		99.7
Sample 3	0	0	0	0	3	4	7		99.6
Sample 4	0	0	0	0	3	3	6		99.7
Sample 5	0	0	0	0	2	3	5		99.7